

Technical Data Sheet



Guaranteed Values

White Kraft Paper Bulky

Brand:

KomiStar

Parameters	Unit of measure	Test method	Substance (g/m ²)						
			60	70	80	90	100	110	120
Substance tolerance	g/m ²	ISO 536	60±3	70±3	80±3	90±3	100±3	110±3	120±3
Moisture tolerance, min/max	%	ISO 287	5.0-8.0						
Bursting strength, min	kPa	ISO 2758	-	250	280	315	330	355	380
Tensile strength MD, min	kN/m	ISO 1924-3	-	5,3	6,0	6,8	7,3	7,7	8,1
Tensile strength CD, min	kN/m	ISO 1924-3	-	2,9	3,3	3,7	4,0	4,3	4,6
Air resistance (Gurley), min/max	sec	ISO 5636-5	20-70						
Cobb ₆₀ (top side), min/max	g/m ²	ISO 535	20-30						
Cobb ₆₀ (bottom side), min/max	g/m ²	ISO 535	20-30						
Brightness, min	%	ISO 2470	100						

Information:

Mill's certificates

- ISO 9001
- ISO 14001
- ISO 45001

Test conditions: Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

Product description:

White Kraft Paper Bulky (with OBA) is made of bleached long fiber sulphate pulp and bleached short fiber sulphate pulp. For the production of carrier bags, consumer bags.

Valid until: 31.12.2025 or until further notice