



Technical Data Sheet



Guaranteed Values

Printing paper

Brand:

KomiText

Parameter	Unit	Test method	Substance	
			55	60
Basis weight	g/m2	ISO 536	55,0 +1,0/-2,0	60,0 +1,0/-2,0
Density	g/cm3	ISO 534	0,6-0,8	
Smoothness	sec	ISO 5627	80-200	
Opacity, min	%	ISO 2471	91	
Moisture	%	ISO 287	7,0-9,0	
Brightness D65/10, min	%	ISO 2470	65	
Ash content, max	%	ISO 2144	14	

Information:

Mill's certificates

- ISO 9001
- ISO 14001
- ISO 45001

Test conditions: Guaranteed values after conditioning measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

System for verifying legal origin of the wood for this product complies with international standard ISO 38200:2018 Chain of custody of wood and wood based products and Forest Certification Legal Origin standard

Product description:

Uncoated mechanical paper without recycled fiber.

Valid until: 31.12.2025 or until further notice