

## **Technical Data Sheet**



## **Guaranteed Values**

## **BLEACHED SOFTWOOD KRAFT PULP**

**Brand:** 

**KomiPrime** 

| Parameter                          | Unit         | Test method  | C1        |
|------------------------------------|--------------|--------------|-----------|
| Brightness, not less               | %            | ISO 3688     | 87.0      |
| Dirt Count (0.1-1.0 mm2), not more | points/500 g | GOST 14363.3 | 25        |
| Dirt Count >1.0 mm2                | points/500 g | GOST 14363.3 | 0         |
| Tearing resistance, not less       | mH·m2/g      | ISO 1974     | 8.0       |
| рН                                 | -            | GOST 12523   | 5.5 - 7.0 |
| Moisture, not more                 | %            | ISO 638      | 15        |
| Breaking Length, not less          | km           | GOST 13525.1 | 7.8       |

## Information:

Mill's certificates

- ISO 9001
- ISO 14001
- ISO 45001

Test conditions: Guaranteed values after conditioning measured at 50  $\pm$  2% RH and 23  $\pm$  1°C (ISO 187)

System for verifying legal origin of the wood for this product complies with international standard ISO 38200:2018 Chain of custody of wood and wood based products and Forest Certification Legal Origin standard

Product description:

BLEACHED SOFTWOOD KRAFT PULP is designed for the production of various types of paper and cardboard.

Valid until: 31.12.2024 or until further notice