

Technical Data Sheet



Guaranteed Values

Newsprint standard

Brand:

KomiPress

Parameter	Unit	Test method	Substance		
			42	45	48,8
Basis weight	g/m2	ISO 536	42,0 ± 1,5	45,0 +1,0/-1,5	48,8 +1,0/-2,0
Density, min	g/cm3	ISO 534	0,6		
Smoothness, min	sec	ISO 5627	60		
Breaking length MD, min	km	ISO 1924-2	4,0	4,5	4,5
Opacity, min	%	ISO 2471	92	93	94
Moisture	%	ISO 287	7,5-9,5		
Brightness D65/10, min	%	ISO 2470	60		
Shade b			4,5-5,5		

Information:

Mill's certificates

- ISO 9001
- ISO 14001
- ISO 45001

Test conditions: Guaranteed values after conditioning measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

System for verifying legal origin of the wood for this product complies with international standard ISO 38200:2018 Chain of custody of wood and wood based products and Forest Certification Legal Origin standard

Product description:

Uncoated mechanical paper without recycled fiber.

Valid until: 31.12.2025 or until further notice