



Technical Data Sheet



Guaranteed Values

Printing paper

Brand:

KomiText

Parameter	Unit	Test method	Substance
			45
Basis weight	g/m2	ISO 536	45,0 +1,0/-1,5
Density	g/cm3	ISO 534	min 0,60
Smoothness	sec	ISO 5627	80-200
Average breaking length MD and CD	m	ISO 1924	min 2500
Moisture	%	ISO 287	7,0-9,0
Brightness D65/10	%	ISO 2470	min 65
Dirt spots 0,1-0,5 mm2	p.	GOST 13525,4	max 200

Information:

Mill's certificates

- ISO 9001
- ISO 14001
- ISO 45001

Test conditions: Guaranteed values after conditioning measured at $50 \pm 2\%$ RH and $23 \pm 1^{\circ}\text{C}$ (ISO 187:1990)

System for verifying legal origin of the wood for this product complies with international standard ISO 38200:2018 Chain of custody of wood and wood based products and Forest Certification Legal Origin standard

Product description:

Uncoated mechanical paper without recycled fiber.

Valid until: 31.12.2024 or until further notice