

KomiPrime

Bleached market pulp



Hardwood pulp

50% birch wood + 50% aspen wood



Discover KomiPrime – our Northern Bleached Hardwood Kraft (NBHK) pulp. It is known for its high quality and is a standard for best products worldwide. The fibers of hardwood pulp are distinguished by their short length and softness enhancing properties of the paper made from this material. These characteristics make hardwood pulp more suitable for certain types of paper products.

Benefits:

- ✓ Outstanding mechanical characteristics
- ✓ Consistent and stable quality with minimal variation in key parameters
- ✓ ECF bleaching: elemental chlorine free pulp bleaching technology helps reduce the mill's negative environmental impact.



Brand: **KomiPrime**

Parameter	Unit	Test method	Guaranteed values	Typical values
Brightness, not less	%	ISO 2470	87.0	88.1
Dirt Count (0.1-1.0 mm²), not more	points/500 g	GOST 14363.3	50	15
Dirt Count >1.0 mm²	points/500 g	GOST 14363.3	0	0
Tear Index, not less	mH·m ² /g	ISO 1974	6.5	7
pH	-	GOST 12523	5.0-7.0	6.3
Moisture, not more	%	ISO 638	15.0	10.2
Breaking Length, not less	km	GOST 13525.1	8.0	8.6

Additional information:

Mill's certificates


- ISO 9001
- ISO 14001
- ISO 45001

Test conditions:
Guaranteed values
after conditioning
measured at 50 ± 2% RH
and 23 ± 1°C (ISO 187)

Product description:


BLEACHED HARDWOOD KRAFT PULP is designed for the production of various types of paper and cardboard.

Refining curve



Bale

	Size 625 x 900 x 500 mm
	Weight 270 kg ± 15
	Packaging Pulp sheets
	Wire 3-4 galvanized wires
	Diameter 2.3 mm



Unit of 6 bales

	Size 1250 x 900 x 1500 mm
	Weight 1620 kg ± 90
	Wire 6-7 windings of galvanized wires
	Diameter 3.0 mm